

Dimension <b>Plank</b>		Dimension <b>Pack</b>		Dimension <b>Pallet</b>	
<b>DIMENSIONS</b>	1900 mm x 190 mm	<b>PACK LENGTH</b>	1920 mm	<b>PALLET LENGTH</b>	19500
<b>THICKNESS</b>	15 mm	<b>PACK WIDTH</b>	198 mm	<b>PALLET WIDTH</b>	1000 mm
<b>TOP LAYER</b>	4.00 mm	<b>PACK THICKNESS</b>	130 mm	<b>PALLET HEIGHT</b>	1145 mm
		<b>PACK WEIGHT</b>	25.70 kg	<b>PALLET WEIGHT</b>	1140,00kg
		<b>PLANKS / PACK</b>	8	<b>PACKS / PALLET</b>	<b>40</b>
		<b>M<sup>2</sup>/PACK</b>	2.888 m <sup>2</sup>	<b>M<sup>2</sup>/PALLET</b>	115.52 m <sup>2</sup>



### Features


#### Top layer

<b>WOOD SPECIES</b>	Oak
<b>LATIN NAME</b>	Quercus Mongolica
<b>CATEGORY</b>	CLASSIC: A rustic floor with knots and slight variations in color, no core defects and occasional traces of sapwood.
<b>CONSTRUCTION</b>	multi-ply or 3 layers solid
<b>THICKNESS</b>	4,00 mm
<b>STRIPS</b>	1
<b>CUTTING METHOD</b>	Sawn veneer
<b>BEVEL</b>	4 sides (0.5 mm)
<b>FINISHING</b>	Smoked , UV oiled or lacquered
<b>SURFACE</b>	Brushed or hand scraped

#### Composition of frame

<b>TYPE</b>	Eucalyptus framework
<b>WOOD TYPE BASIS</b>	Eucalyptus & Poplar
<b>CONSTRUCTION BASIS</b>	7-9 layers cross lay
<b>TOTAL THICKNESS OF FRAME</b>	11mm
<b>ADHESIVE</b>	Dynea

#### Steps

SYSTEM	APPLICATION	UNDERFLOOR HEATING
Tongue and groove system 	Light household use Normal household use Moderate commercial use Normal commercial use Intensive commercial use	Yes <b>RE-SANDABLE</b> Yes
		More info on <a href="http://www.styletimberfloor.com.au">www.styletimberfloor.com.au</a> "Euro oak mimano collection"

### Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and Multilayer parquet elements)

Assessed property	Classification or test method	Requirement	Result or classification	Evaluation
Release of formaldehyde	EN 717-1	$\leq 0.124$ mg/m <sup>3</sup>	$\leq 0.014$ mg/m <sup>3</sup>	E0
Width-permit deviation	EN 13647	$\pm 0.2$ mm	-0.1mm	Fulfil
Moisture content	EN 13183-1	9 $\pm$ 2%	7.0%	Fulfil
Reaction to fire(floor)	AS ISO 9239.1-2003	CRF $\geq$ 4.5KW/m <sup>2</sup>	6.9 KW/m <sup>2</sup>	Fulfil
Reaction to fire (wall& ceiling)	AS/NZS 3837:1998	Group number 1-4	Group number 3	Middle range
Sliptest-Wet Pendulum	AS 4586&4663 (2013)	P1-P5	P2	Middle range
Hardness	Janka Rating	None	1360	Middle range

### Technical Specifications

- Additional tests:

-Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)

-The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)