

Dimension Plank		Dimension Pack		Dimension Pallet	
DIMENSIONS	1900 mm x 190 mm	PACK LENGTH	1920 mm	PALLET LENGTH	19500
THICKNESS	15 mm	PACK WIDTH	198 mm	PALLET WIDTH	1000 mm
TOP LAYER	4.00 mm	PACK THICKNESS	130 mm	PALLET HEIGHT	1145 mm
		PACK WEIGHT	25.70 kg	PALLET WEIGHT	1140,00kg
		PLANKS / PACK	8	PACKS / PALLET	40
		M²/PACK	2.888 m ²	M²/PALLET	115.52 m ²



Features


Top layer

WOOD SPECIES	Oak
LATIN NAME	Quercus Mongolica
CATEGORY	CLASSIC: A rustic floor with knots and slight variations in color, no core defects and occasional traces of sapwood.
CONSTRUCTION	multi-ply or 3 layers solid
THICKNESS	4,00 mm
STRIPS	1
CUTTING METHOD	Sawn veneer
BEVEL	4 sides (0.5 mm)
FINISHING	Smoked , UV oiled or lacquered
SURFACE	Brushed or hand scraped

Composition of frame

TYPE	Eucalyptus framework
WOOD TYPE BASIS	Eucalyptus & Poplar
CONSTRUCTION BASIS	7-9 layers cross lay
TOTAL THICKNESS OF FRAME	11mm
ADHESIVE	Dynea

Steps

SYSTEM	APPLICATION	UNDERFLOOR HEATING
Tongue and groove system 	Light household use Normal household use Moderate commercial use Normal commercial use Intensive commercial use	Yes RE-SANDABLE Yes
		More info on www.styletimberfloor.com.au "Euro oak mimano collection"

Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and Multilayer parquet elements)

Assessed property	Classification or test method	Requirement	Result or classification	Evaluation
Release of formaldehyde	EN 717-1	≤ 0.124 mg/m ³	≤ 0.014 mg/m ³	E0
Width-permit deviation	EN 13647	± 0.2 mm	-0.1mm	Fulfil
Moisture content	EN 13183-1	9 \pm 2%	7.0%	Fulfil
Reaction to fire(floor)	AS ISO 9239.1-2003	CRF \geq 4.5KW/m ²	6.9 KW/m ²	Fulfil
Reaction to fire (wall& ceiling)	AS/NZS 3837:1998	Group number 1-4	Group number 3	Middle range
Sliptest-Wet Pendulum	AS 4586&4663 (2013)	P1-P5	P2	Middle range
Hardness	Janka Rating	None	1360	Middle range

Technical Specifications

- Additional tests:

-Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)

-The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)